

The present invention relates to a plasma torch electrode, formed from an electrode body that includes a cavity into which an emissive hafnium/zirconium insert is fitted, and to a plasma torch comprising the
5 said electrode.

The process of cutting structural steels, that is to say non-alloy or low-alloy carbon steels, or even stainless steels and aluminium alloys, by means of a
10 plasma arc in an oxygen atmosphere has been known for many years.

A plasma cutting device capable of implementing such a process generally comprises a plasma cutting torch
15 comprising a nozzle for ejecting the plasma arc towards the workpiece to be cut, an electrode that forms the cathode, placed a certain distance from the nozzle and coaxially therewith, a supply of plasma gas, such as compressed air, oxygen or any other gas mixture
20 containing at least one oxidizing gas, and a means of delivering the plasma gas into the volume separating the electrode from the nozzle, also called a plasma chamber.

25 The workpiece itself forms the anode, the cathode and the anode being connected to the terminals of a current generator.

To promote the striking of the arc and to limit high-
30 temperature erosion of the electrode in an oxidizing atmosphere, which electrode is typically made of copper or a copper alloy, it is customary to provide the electrode with an emissive insert, made of zirconium or, depending on the case, hafnium, fitted, coaxially,
35 into the end facing the ejection orifice of the nozzle.

Zirconium is a less expensive material than hafnium, but less resistant to high-temperature erosion by the plasma arc.

Conversely, pure hafnium has the best resistance to erosion by the plasma arc, but is very expensive, especially because of the fact that, in order to be
5 able to obtain pure hafnium, it is necessary to "refine" it during its manufacture so as to remove the impurities that contaminate this material.

Although reputed to have a longer lifetime, electrodes
10 provided with an emissive insert made of pure hafnium wear away in a few hours, typically between 2 and 4 hours, when they are used in a plasma cutting torch.

These electrodes with a hafnium or zirconium emissive
15 insert therefore constitute a consumable item of the torch that it is necessary to replace often, which therefore increases the overall cost of the process and poses problems from the industrial standpoint since, to replace the electrode, it is necessary to stop the
20 insulation and dismantle the front part of the torch.

The problem to be solved is therefore how to provide an emissive electrode insert having a lifetime close to that of electrodes with a pure hafnium insert but for a
25 lower manufacturing cost.

The solution provided by the invention is therefore an emissive electrode insert formed from an alloy containing hafnium and zirconium.

30 Depending on the case, the emissive insert of the invention may have one or more of the following technical features:

- 35 - it contains at least 80% hafnium by weight, preferably at least 90% hafnium by weight;
- it contains 0.1 to 8% zirconium by weight, preferably 0.5 to 5% zirconium by weight;

- it contains 96 to 99% hafnium by weight, 0.5 to 3.5% zirconium and inevitable impurities for the balance;

- it contains 98.08 to 98.20% hafnium by weight, 1.70 to 1.82% zirconium and inevitable impurities for the balance;

- it is of cylindrical shape; and

- it has a length of 3 mm to 8 mm and a diameter of 1 mm to 4 mm.

10

According to another aspect, the invention also relates to a plasma torch electrode formed from an electrode body, comprising a cavity into which an emissive insert according to the invention is fitted, preferably an electrode made of copper or a copper alloy, and to a plasma torch comprising such an electrode, preferably a plasma cutting torch for cutting a workpiece made of steel, in particular structural steel.

20

The present invention will be more clearly understood thanks to the description below, given with reference to the illustrative figures appended hereto.

25

Figure 1 is a diagram in a longitudinal sectional view, of an electrode 1 with a solid body consisting of an electrode body 2, of axisymmetric general shape in the form of a cup with a blind hole, which body has, in its upper or upstream part, an internal thread 4 for allowing the electrode 1 to be screwed onto a torch body; in its lower part, or active part, a bore 6' for housing, by being force-fitted, by being crimped and/or by being brazed, an emissive insert 3 made of a hafnium/zirconium alloy according to the invention; and having, in its central part 5, a polygonal, especially hexagonal, external shape so as to take a spanner of suitable shape in order for the electrode 1 to be screwed tightly onto its support in the torch body.

35

The electrode 1 is made of a copper alloy of the copper/tellurium type, having a tellurium content of about 0.3 to 0.7%, or of the copper/chromium/zirconium type, the balance essentially being copper and possibly
5 inevitable impurities.

Figure 2 shows an electrode 1 of high mechanical strength, of general shape similar to that of Figure 1 (the similar or identical parts bear the same
10 references) having, in its central part 5, a prismatic or semi-prismatic external shape for taking a spanner of suitable shape in order to screw the electrode 1 onto its support in the torch body and lock it therein.

15 Moreover, a groove 7, intended to house an O-ring seal, is made between the thread 4 and a bearing surface 8 that forms an assembly stop.

Such an electrode has a high thermal withstand since
20 the use of a copper alloy of the copper/chromium type for producing the electrode 1 allows its geometrical integrity to be maintained, especially close to the emissive insert 3, that is to say without local melting, despite a high temperature at the active end
25 carrying the insert 3.

Within the context of the invention, the insert 3 fitted into the electrodes 1 is made of a hafnium/zirconium alloy.

30

This is because, in order to guarantee an acceptable lifetime of the electrodes 1 with an insert 3 without this being to the detriment of the cost of the process, the emissive insert 3 according to the invention must
35 be made of a hafnium/zirconium alloy.

To do this, incompletely refined hafnium may be used, in which a controlled proportion of zirconium and possibly other residual impurities, for example Fe, Al,

N, Cr, W, Mn, Ta, Si, Mn, O, U, Ti, Nb, Cu, Sn, V, Co, Mg, Ni, Pb, Mo, etc., are intentionally left, the content of each of these inevitable impurities generally never exceeding 0.01% by weight, or even only
5 a few ppm.

It is also possible to use pure hafnium to which a desired proportion of zirconium by weight is added so as to obtain an Hf/Zr alloy in the proportions of the
10 invention, that is to say preferably 96 to 99% hafnium by weight, 0.5 to 3.5% zirconium and inevitable impurities for the balance (about 0.5%), advantageously 98.08 to 98.2% hafnium by weight, 1.7 to 1.82% zirconium and inevitable impurities for the balance
15 (0.027 to 0.1%).

The insert 3 preferably has a cylindrical general shape and is fitted into the electrode body by crimping or the like.

20 A plasma cutting torch, with the reference OCP 150 sold by La Soudure Autogène Française, was equipped with an electrode made of a copper alloy, such as an electrode according to Figure 1 or 2, fitted with an insert made
25 of a hafnium/zirconium alloy according to the invention (approx. 98.1% Hf by weight + 1.82% Zr by weight + impurities for the balance) and was then subjected to a succession of cutting sequences using oxygen as cutting gas until the insert and/or the electrode were
30 extremely worn.

The material to be worked was a plate of structural steel 10 mm in thickness. The cutting current was
35 120 amps.

These trials have shown that an electrode according to the invention has a lifetime of around 4 hours with 500 striking operations, which is equivalent to the lifetime of electrodes with a pure hafnium insert.